



SelectLine Printing Blanket

	2360Htype	2300type	2100H type	5200 type (underblanket)	UV blanket
Application	Sheet-fed press	Sheet-fed press	Sheet-fed press		Sheet-fed press
Surface	Buffed	Buffed	Buffed	Buffed	Buffed
color	Blue	Blue	Blue	Black	Blue
Surface Roughness	about 0.9u (N/mm ²)	about 0.9u (N/mm ²)	about 0.9u (N/mm ²)		about 0.9u (N/mm ²)
Thickness	1.95mm+/-0.02mm	1.95mm+/-0.02mm	1.95mm+/-0.02mm	1.00mm+/-0.02mm	1.95mm+/-0.02mm
Hardness	about 77 shore A	about 77 shore A	about 75 shore A	about 58 shore A	about 77 shore A
Elongation	<0.7% (500N/5cm)	<1% (500N/5cm)	<1.5% (500N/5cm)		<0.7% (500N/5cm)
Tensile Strength	>4500N/50mm	>4600N/50mm	>4500N/50mm		>4500N/50mm
Compressibility	0.20mm at 200N/cm2	0.20mm at 200N/cm2	0.20mm at 200N/cm2		0.20mm at 200N/cm2
For convetional ink	*	*	*		
For UV ink					*
Ply:				2	

- Low dot gain
- Best contrast values
- Outstanding results in solid and half-tone printing

- Optimized surface for high-quality half tone, solid print, low dot gain and best contrast values

- High stability due to four-ply carcass

